



2041 Dillard court

PH 815.337.2349

Woodstock, IL 60098

info@shannonindustrial.com

**15 MELT COPOLYMER POLYPROPYLENE
FDA COMPLIANT**

PROPERTIES		ASTM METHOD
Melt Flow Rate, 230/2.16, g/10 min	15.0	D1238
Density, g/cm³	0.920	D1505
Tensile Strength at Yield, psi	3,500	D638
Flexural Modulus 1% Secant At .05 in/min, psi	150,000	D790A
Notched Izod Impact Strength Ft/lb/in @ 73°	2.5	D256A
Heat Deflection Temperature, F°@ 66 psi	82C	D648