



CPP-20-2IZ COPOLYMER POLYPROPYLENE

PROPERTIES	ASTM METHOD	
Melt Flow Rate, 230/2.16, g/10 min	18.0-22D1238	
Density, g/cm³	0.88-.92	D1505
Tensile Strength at Yield, psi	3,000-3200	D638
Flexural Modulus 1% Secant At .05 in/min, psi	140,000-160,000	D790A
Notched Izod Impact Strength Ft/lb/in @ 73°	1.90-2.20	D256A
Heat Deflection Temperature, F°@ 66 psi	203	D648