



GPPS NATURAL 14 MELT

Melt Flow Rate, g/10 min	ASTM D1238	14.0
Tensile Strength @ FAILURE psi	ASTM D638	6,900
Elongation @ Yield %	ASTM D638	1
Rockwell Hardness, L Scale	ASTM D785	71
Izod Impact Strength	ASTM D256	.25
Deflection Temperature @264psi	ASTM D648	185 deg F
Specific gravity	ASTM D892	1.05 gr./cc

