



## GPPS NATURAL 18 MELT

<b>Melt Flow Rate, g/10 min</b>	<b>ASTM D1238</b>	<b>18.0</b>
<b>Tensile Strength @ FAILURE psi</b>	<b>ASTM D638</b>	<b>6,900</b>
<b>Elongation @ Yield %</b>	<b>ASTM D638</b>	<b>1</b>
<b>Rockwell Hardness, L Scale</b>	<b>ASTM D785</b>	<b>71</b>
<b>Izod Impact Strength</b>	<b>ASTM D256</b>	<b>.25</b>
<b>Deflection Temperature @264psi</b>	<b>ASTM D648</b>	<b>185 deg F</b>
<b>Specific gravity</b>	<b>ASTM D892</b>	<b>1.05 gr./cc</b>

