



GENERAL PURPOSE HOMO PP 30MELT Antistatic, Nucleated, General Purpose HOMOPOLYMER POLYPROPYLENE

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

Density	ASTM D792B	0.90
Melt Flow Rate	ASTM D1238	30
Tensile Strength at Yield (50mm/ min), psi	ASTM D638	5,300
Tensile Elongation at Yield, psi	ASTM D638	9
Flexural Mod. (1.3 mm/ min), 1% Secant, psi	ASTM D790	270,000
Notched Izod Impact Str. @ 73 F, ft-lb/in	ASTM D256A	0.7
Hardness, Rockwell R	ASTM D 785A	95