



GPPS CLEAR

Melt Flow Rate, g/10 min	ASTM D1238	8-10
Tensile Strength @ FAILURE psi	ASTM D638	4,300-6,200
Elongation @ Yield %	ASTM D638	1
Rockwell Hardness, L Scale	ASTM D785	71
Izod Impact Strength	ASTM D256	.30
Deflection Temperature @264psi	ASTM D648	185 deg F
Specific gravity	ASTM D892	1.04 gr./cc

