



SHANNON INDUSTRIAL CORP

PH 815 337 2349

info@shannonindustrial.com

POLYLAC® PA-709

Acrylonitrile Butadiene Styrene

[CHI MEI CORPORATION](#)

Product Description:

POLYLAC® PA-709 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Impact Resistant

Injection	Nominal Value	Unit
Drying Temperature	80 to 85	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	180 to 220	°C
Middle Temperature	190 to 230	°C
Front Temperature	190 to 230	°C