



## POLYLAC PA-747F - ABS

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	3	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	1	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	0.3	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	0.5	kg	-
Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	46	MPa	ISO 527
Stress at break	35	MPa	ISO 527
Flexural modulus, 23°C	1900	MPa	ISO 178
Charpy notched impact strength, +23°C	27	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness	99	MPa	ISO 2039-1
<b>ASTM Data</b>			
Tensile Strength	46.1	MPa	ASTM D 638
Flexural Modulus	2620	MPa	ASTM D 790
Flexural Strength	75.2	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785
Izod Impact notched, 1/8 in	368	J/m	ASTM D 256
Izod Impact notched, 1/4 in	294	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	89	°C	ISO 75-1/-2
Vicat softening temperature, A	106	°C	ISO 306
Vicat softening temperature, B	101	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
Vicat Temperature	106	°C	ASTM D 1525
Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183
Density	1050	kg/m <sup>3</sup>	ASTM D 792

### Processing

Other Extrusion

### Delivery form

Pellets

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Refrigeration

### Regional Availability

Asia Pacific

