



## PROLINE PC 1707R-112 NON UV STABILIZED POLYCARBONATE

Property	ASTM	ENGLISH NOMINAL VALUES
Melt Flow, g/10 minutes 300° C, 1.2 kg	D1238	7
Izod Impact Ft-lb/in	D256	17
Tensile Strength @ yield,psi	D638	9,000
Flexural Modulus Psi	D790	340,000
Specific Gravity	D792	1.2
Mold Shrinkage	D955	.006

