



PROLINE 1620 LDPE NATURAL

PROPERTY	ASTM METHOD	VALUE
Melt Flow, g/10 min	ASTM D1238	16
Density, g/cm³	ASTM D1505	0.920
Elongation @ break, %	ASTM D638	375.0
Tensile Modulus, psi	ASTM D638	40,000
Tensile Strength @ break, psi	ASTM D638	1250
Tensile Strength @ yield, psi	ASTM D638	1650
Hardness, Shore D	ASTM D2240	45
Vicat Softening Point, °F	ASTM D1525	187