



PROLINE 18 MELT HOMOPOLYMER POLYPROPYLENE

PROPERTIES		ASTM METHOD
Melt Flow Rate, I ² @ 230°C, g/10 min	18.0	D1238
Density, g/cm ³	0.900	D792
Tensile Strength at Yield, psi	5,100	D638
Flexural Modulus, psi	270,000	D790
Notched Izod Impact Strength Ft-lb/in @ 73°F	0.6	D256A
Heat Deflection Temperature F° @ 66 psi	194	D648