



SHANNON PROLINE 30% GF COPOLYMER POLYPROPYLENE

PROPERTY	AVERAGE VALUES	ASTM METHOD
Fiberglass Content, %	30	
Melt Flow, g/10 min.	2-4	D1238
Specific Gravity, g/cm ³	1.13	D792
Tensile Strength, psi @ 73°F	8,500	D638
Flexural Modulus, (Tangent) psi	600,000	D790
Izod Impact, ft-lb/in @ 73°F Notched ½" x 1/8"	1.8	D256
Gardner Impact, in-lb	15	D3029
Heat Deflection, °F @ 264 psi @66 psi	270 240	D648
Hardness Shore "D"	75	D2240