



**PROLINE CG960
HIGH DENSITY POLYETHYLENE**

PROPERTY	TEST METHOD	VALUE
Melt Index, g/10min.	ASTM D1238	.35
Density, g/cm3	ASTM D1505	.955
Tensile Strength @ Yield, psi	ASTM D638	4,000
Flexural Modulus, psi	ASTM D790	200,000
Elongation @ Break, %	ASTM D638	600