



Proline GPC 12

General Purpose Copolymer Polypropylene

| PROPERTIES | ASTM METHOD | |
|---|--------------------|-----------------------|
| Melt Flow Rate, I @ 230°C, g/10 min | D1238 | 12.0 |
| Density, g/cm³ | D1501 | 0.900 |
| Notched Izod Impact Str. @ 73°F, ft-lb/in(J/m) | D256 | 2.0 (107) |
| Tensile Strength at yield, psi (MPa) | D638 | 3,800(26) |
| Elongation at Yield, % | D638 | 7 |
| Flexural Modulus, psi (MPa) | D790 | 170,000(1,170) |
| Rockwell Hardness, R Scale | D2240 | 105 |