



Proline GPC 17-2 Copolymer Polypropylene

Melt Flow Rate, I2 @ 230°C, g/10 min ASTM D1238		17.0
Density, g/cm3	ASTM D1505	0.900
Tensile Strength @ Yield (50 mm/min),psi	ASTM D638	3,400
Elongation @ Yield (50 mm/min), %	ASTM D638	7
Flexural Mod. (1.3 mm/min), 1% Secant, psi	ASTM D790	160,000
Rockwell Hardness, R Scale	ASTM D785	105
Notched Izod Impact Strength @ 73°F, ft-lb/in	ASTM D256	3.0
Notched Charpy Impact Strength @ 73°F, ft-lb/in	ASTM D256	2.8