



## PROLINE GPC 18 MELT COPOLYMER POLYPROPYLENE FDA COMPLIANT

PROPERTIES		ASTM METHOD
Melt Flow Rate, 230/2.16, g/10 min	18.0	D1238
Density, g/cm <sup>3</sup>	0.902	D1505
Tensile Strength at Yield, psi	3,000	D638
Flexural Modulus 1% Secant At .05 in/min, psi	150,000	D790A
Notched Izod Impact Strength Ft/lb/in @ 73°	NB	D256A
Heat Deflection Temperature, F° @ 66 psi	85C	D648