



## PROLINE GPC-20-30 COPOLYMER POLYPROPYLENE

<b>Melt Flow Rate, I<sup>2</sup> @ 230°C, g/10 min</b>	<b>ASTM D1238</b>	<b>20.0-30.0</b>
<b>Density, g/cm<sup>3</sup></b>	<b>ASTM D1505</b>	<b>0.900</b>
<b>Tensile Strength at Yield (50 mm/min), psi</b>	<b>ASTM D638</b>	<b>3,200</b>
<b>Flexural Mod. (1.3 mm/min) 1% Secant, psi</b>	<b>ASTM D790</b>	<b>135,000</b>
<b>Rockwell Hardness, R Scale</b>	<b>ASTM D785</b>	<b>100</b>
<b>Notched Izod Impact Strength @ 73° F, ft-lb/in</b>	<b>ASTM D256</b>	<b>5.0</b>