



PROLINE 5408 HDPE

	Nominal Values	Test
Density	0.954 g/cm³	ASTM D1505
Melt Flow Rate	7 g/10 min	ASTM D1238
Tensile Strength @ Yield	4100 psi	ASTM D638
Tensile Strength @ Break	3250 psi	ASTM D638
Flexural Modulus	181000 psi	ASTM D790