



Proline NYLON P66 GP Natural

Property	ASTM	EnglishMetric	
Melt Point		496°	258°
Izod Impact ft-lb/in (J/m)	D258	.9	48
Tensile Strength @ yld,psi (Mpa)	D638	12000	83
Flexural Modulus psi, (Mpa)	D790	450,000	3103
Specific Gravity	D792	1.14	n/a
Mold Shrinkage in/in	D955	.014	n/a
HDT 66 psi	D648	428°	220°
264 psi		149°	65°

