



PROLINE GPC- 30 COPOLYMER POLYPROPYLENE

Melt Flow Rate, I² @ 230°C, g/10 min	ASTM D1238	30.0
Density, g/cm³	ASTM D1505	0.900
Tensile Strength at Yield (50 mm/min), psi	ASTM D638	3,200
Flexural Mod. (1.3 mm/min) 1% Secant, psi	ASTM D790	135,000
Rockwell Hardness, R Scale	ASTM D785	100
Notched Izod Impact Strength @ 73° F, ft-lb/in	ASTM D256	3.0